

Lloyd's Register of Shipping.

Order: 8984.

Surveyors' Office, DÜSSELDORF.

Gothenburg report N° 7328

This is to certify, that

the works of

the

by

for the ship No.

Kalle Berg

Gütschaffningsschutte A. G.

annealed Siemens Martin Boilersteel plates

Hessan A. B. Göttercken

STARTING AIR RECEIVERS
Boiler No.

the undersigned surveyor to this society tested in

of Oberhausen

specified hereunder, ordered

of Gothenburg

and that the results of tests were as are set forth below.

Sample number.	Dimensions. in mm			Intended for	Sample number	Charge number	Tensile tenacity kg. p. sq. mm			Elongation in 200 mm. in %	Bending tests		Remarks.
	Length.	Breadth.	Thick-ness.				As per rules.	Ord-ered.	By test.		Cold.	Tem-pered.	
1	5930	2810	25.5	Shell pl.	3	46513	44/55	44/50	46.6	24	good	good	Lloyd's.
					3				48.8	24	"	"	
1	"	"	"	" "	4	"	"	"	48.5	26	"	"	
					4				45.2	24	"	"	
1	5440	"	25	" "	2	"	"	"	45.4	24	"	"	
					2				48.4	24	"	"	
1	"	"	"	" "	24	46635	"	"	48.4	25	"	"	
					24				45.4	28	"	"	
2	900	430	19		26	46506		"	44.5	23	"	"	
2	2810	420	25.5	Brillt skaps	4		44/55	"	45.2	24	"	"	
2	2425	410	"	" "	23	46513	"	"	46.4	29	"	"	
2	2650	"	25	" "	20	46330	"	"	44.8	28	"	"	
2	2585	420	"	" "									
1	To sketch		26.5	End pl.	12	46562	44/44	44/44	44.6	28	"	"	2295
					12				43.0	28	"	"	
1	"	"	"	" "									2296
1	"	"	"	" "	14	46562	"	"	45.9	24	"	"	2312
					14				43.2	28	"	"	
1	"	"	"	" "									2303
1	980	460	25	Comp. ring	22	46515	"	"	42.9	24	"	"	2283
1	"	"	"	" "									2284
1	500	400	40	Hatch door	21	"	"	"	43.0	30	"	"	2289
1	"	"	"	" "									2290

This Certificate is issued upon the terms of the Rules and Regulations of the Society, which provide that

"While the Committee use their best endeavours to ensure that the functions of the Society are properly executed, it is to be understood that neither the Committee nor the Society are under any circumstances whatever to be held responsible for any inaccuracy in any report or certificate issued by the Society or its Surveyors, or in any entry in the Register Book or other publication of the Society, or for any error of judgment, default, or negligence of the Surveyors, or other Officers or Agents of the Society."

N.B.—Material with less than 26 Tons tensile strength may not be used in the construction of boilers for classed vessels, unless specially sanctioned by the Committee.

1 Ton per square inch = 1,574 Kilo per square millimeter. 1 Kilo per square millimeter = 0,635 Tons per square inch.

W1088-0185