

Lloyd's Register of Shipping.

(Report on Vessel No. _____ Port _____)

No. 314

SHIP FORGINGS OR CASTINGS.

I have to report that the undermentioned ~~Iron or Steel Forgings or Castings~~, manufactured by The Matsuo Iron Works, Yokohama of Nagasaki for the Vessel No. 57, being built by them of _____ have been inspected by me as set forth below and found to be, so far as can be seen, sound, and free from defects.

Mark on Forgings or Castings.

Lloyd's

No. 314

A.S.W.

Nagasaki, 13th Sept. 1917

a. J. Williamson

	STERN FRAME.	RUDDER FRAME.	STEM.
Material*		S. M. C. Steel	
How made		Forged	
Dimensions		8"	
Progress on Inspection		When being forged & machined	
Date when Inspected		28/7/17 to 11/9/17	
CASTINGS.			
Tests on Standard Test Pieces.			
Tensile Test—			
Tons per square inch	31.3 & 31.1 tons	32.5 & 31.8 tons	
Extension per cent.	34.4 & 31.3%	32.5 & 31.3%	
Cold Bending Test—			
Angle before fracture	180°	180°	
Drop Test—			
Height from ground	✓	✓	
Hammering Test—			
If made according to Rules and found satisfactory	✓	✓	

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Fee (if any chargeable) £ _____

To be paid at _____

* If of Iron, state whether scrap or puddled Iron. If of steel, state whether made on the Open Hearth process.

Rept- N^o 1143
Nagasaki.

© 2020

Lloyd's Register
Foundation

413.076
W.2.A

W. S. A.

W. S. A.

11/11/11

1894

2.2.2
 2.2.2
 2.2.2

22

1000

1.16. 8.16.

10

12

2007-08-08

MASTIS, STAFF, & CO.