

W1109-0210

C O P Y for LONDON Office.

LLOYD'S REGISTER OF SHIPPING

Surveyors' Office DUSSELDORF

Order N°18288

Copy of material tested by Josef Loogen Surveyor to  
Lloyd's Register at the Works of Messrs. Friedr Krupp A.C. of  
Armen & ordered by Messr Ottensener Eisenwerke. per Boiler  
NO.C/20.

N°	Thick- ness	Intended for	Stamped on mater- ial.	Tensile As per Rules.	Tenacity Order- ed	By test	Elen in 200 mm %	Bending tests Cold Ten
rs.	40,02	C.C.stays	1 300 E	41-47	41-47	44,2	28,0	Good G
	50,0"	" "	2 " "	" "	" "	42,0	28,0	" "
	60,0"	" "	5 607 B	" "	" "	42,0	29,0	" "
	70,0	" "	3 606 B	" "	" "	45,6	25,0	" "
	80,0	Long.Stays	4 606 B	44-53	44-50	45,7	25,0	" "

Dusseldorf 10th June 1925

(Sgd) J. Loogen

Surveyor to Lloyd's Register.

15.07.1926



© 2020

Lloyd's Register  
Foundation