

Lloyd's Register of Shipping.

Order: 368609.

(Report on Vessel No. 16726Port Hamburg)No. 2087.

SHIP ~~XXXXXXXXXXXX~~ FORGINGS OR CASTINGS.

I have to report that the undermentioned ~~XXXXXX~~ Steel ~~XXXXXX~~ Castings, manufactured by **Messrs. Fried. Krupp A.G.**

of **Essen**for the Vessel No. **480/81**, being builtby **Messrs. Germaniaerft**of **Kiel-Gaarden**

have been inspected by me as set forth below and found to be, so far as can be seen, **1 stem shoe and 1 casting for a keel construction sound and free from surface defects.**

on Forgings or Castings.

Lloyd's

Düsseldorf 16th February 1925.

No. 278/277.

M.B.6.2.25.


	277	278
	1 casting for a RUDER FRAME keel construction Annealed Siem. Mart. Cast Steel cast	1 STEM. shoe cast
STERN FRAME.		
Material		
made		
Inspections		
Process on Inspection	rough turned	rough turned
when Inspected	6.2.25.	6.2.25.
CASTINGS.		
on Standard Test Pieces.	.798 3"	.798 3"
Re Test—		
tons per square inch	30,1	30,1 29,9
Extension per cent.	36,0	33,0 33,3
Bending Test—		
angle before fracture	120 degr. good	120 degr. good
Test—		
Height from ground	10 feet	10 feet
Finishing Test—		
made according to Rules and found satisfactory	satisfactory	satisfactory

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Fee (if any chargeable) £

To be paid at **Düsseldorf**.

of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.



© 2020

Lloyd's Register
Foundation

N1151 - 0015

42/43