

VESSEL'S NAME **S.S. "SANTOFF"**Report **Baltimore** No. **7743**

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

decimals

The thicknesses are in / of an inch.

STRAKE.	AMIDSHIP.				FORWARD.				AFT.				REMARKS.		
	Original Thickness.	Thickness by drilling.		Diminution if any.	Original Thickness.	Thickness by drilling.		Diminution if any.	Original Thickness.	Thickness by drilling.		Diminution if any.			
		Port.	Std.			Port.	Std.			Port.	Std.			Port.	Std.
SPAR SHEER STRAKE															
Strake below.....															
MAIN SHEER STRAKE	1.00	1.03	1.03	-	-	.70	.72	.72	-	-	.60	.60	.62	-	-
1st Strake below85	.87	.87	-	-	.64	.65	.65	-	-	.56	.55	.56	.01	-
2nd " "66	.65	.62	.02	.04	.54	.56	.50	-.04	.50	.48	.50	.02	-	
3rd " "66	.62	.62	.04	.04	.54	.50	.50	.04	.04	.54	.46	.45	.08	.08
4th " "66	.75	.56	-	.10	.54	.56	.50	-	.04	.50	.54	.50	-	-
5th " "66	.53	.59	.13	.07	.54	.56	.56	-	-	.50	.46	.46	.04	.04
6th " "66	.62	.65	.04	.01	.50	.50	.56	-	-	.50	.56	.50	-	-
7th " "66	.59	.62	.07	.04	.52	.50	.50	.02	.02	.54	.56	.54	-	-
8th " "66	.65	.62	.01	.04	.66	.59	.62	.07	.04	.52	.50	.50	.02	.02
9th " "66	.65	.62	.01	.04	.66	.62	.62	.04	.04	.66	.62	.62	.04	.04
10th " "66	.62	.56	.04	.10	.66	.62	.62	.04	.04					
11th " "66	.62	.56	.04	.10										

Drillings at ends to be made in the vicinity of the peak bulkheads.

© 2020

Lloyd's Register

Foundation

W1196-0015