

Lloyd's Register of Shipping.

(Report on Vessel No.

85

Port

Seattle, Wash.

No.

SHIP ~~FORGINGS OR~~ CASTINGS.

I have to report that the undermentioned Iron or Steel Forgings or Castings, manufactured by new Seattle Ste. Co.

of St. Louis Mo.for the Vessel No. 85

being built

by The Seattle Dry Dock Co.

of

Seattle Wash

have been inspected by me as set forth below and found to be, so far as can be seen, Satisfactory

on Forgings or Castings.

Lloyd's

No. 1118-1-16 J.D.Chicago 31st January 1916

(Signed) J. Darby.

Wm. H. S. Gardiner

	STERN FRAME.	RUDDER FRAME.	STEM.
Material* ...		Cast Steel	
made ...		Eutectic process	
Dimensions ...			
Progress on Inspection ...		When finished	
when Inspected ...		19 th Jan. 1916	
CASTINGS.			
Tests on Standard Test Pieces.			
Side Test—		60000	
Tons per square inch ...		35% w 2"	
Extension per cent. ...		120° without F.	
Bending Test—		Through 45°	
Angle before fracture ...		Yes.	
Test—			
Height from ground ...			
Emerging Test—			
If made according to Rules and found satisfactory ...			

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Fee (if any charged) \$ 32.47To be paid at Chicago

If of Iron, state whether scrap or puddled Iron. If of steel, state whether made on the Open Hearth process.

T.

© 2020

Lloyd's Register

Foundation

W1214-0123