

S/S "HEIYO MARU" (O.I.W.961

RUDDER STOCK:- Osaka Iron Works Forging

TEST MARK 962-S

Tensile & elongation 29.1 tons 35% Bend good.

Dates of test 20/12/19

Final Stamped

962-S  
LLOYDS  
22-4-20  
Y.J.R.

No Certificate  
issued.

MAIN PIECE - Sumitomo Steel Works Forging.

TEST MARK R 98.

R 98  
LLOYDS  
28.6.18  
ALJ.LR  
V49  
LR  
15.3.18  
ALJ



© 2020

Lloyd's Register  
Foundation