

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office, \_\_\_\_\_

# Lloyd's Register of Shipping.

(Report on Machinery, No. \_\_\_\_\_ Port \_\_\_\_\_)

No. 140

## ENGINE FORGINGS OR CASTINGS.

I have to report that the Iron or Steel Forgings or Castings, as herein described, manufactured by Nova Scotia Steel Coal Co. of New Glasgow, N.S. for the Engines No. \_\_\_\_\_ being constructed by Canadian Vickers Montreal for the Ship No. 69, being built by \_\_\_\_\_ of \_\_\_\_\_

have been inspected by me as set forth below, and found to be, so far as can be seen, sound

*A. Jones*  
New Glasgow.

ings or Castings.

Lloyd's

427  
7.18

480  
31. 9.18  
0. T. J.

390  
7. 6.18  
0. T. J.

405  
9. 8. 18  
0. T. J.

Line	CRANK SHAFT.	STRAIGHT SHAFTING.		
		Line	Line	Line
		THRUST SHAFT.	INTERMEDIATE SHAFTS.	PROPELLER SHAFT.
<u>O.N. Steel</u>				
<u>Forged</u>	<u>Forged</u>	<u>Forged</u>	<u>Forged</u>	<u>Forged</u>
<u>Forged &amp; R.D.</u>				
Standard pieces.	<u>67480</u>	<u>64500</u>	<u>70000</u>	<u>68800</u>
Weight square inch	<u>31</u>	<u>32</u>	<u>30.5</u>	<u>33</u>
Per cent	<u>180</u>	<u>180</u>	<u>180</u>	<u>180</u>
Weight Test— fracture	<u>June 13, 25</u>	<u>Aug. 23, 31</u>	<u>May 15, 22,</u>	<u>May 28, 30,</u>
Inspected	<u>July 12/18.</u>	<u>Sept 21/18.</u>	<u>June 9/18</u>	<u>Aug. 9/18.</u>

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(any chargeable) £ \_\_\_\_\_  
to be paid at \_\_\_\_\_

state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.

