

N^o 7457. Amended. Report.

Lloyd's Register of Shipping.

RESULTS OF TESTS OF STEEL.

Made by Messrs Vickers L^{td}, Sheffield

For Messrs Vickers L^{td}, Barrow in Furness.

Engines N^o 572

St.	Batch No.	Test No.	Change Mark	Thickness. LLOYD'S N ^o	Breadth.	Area.	Tens. Total.	Tons per square inch.	Extension in 3" ins. ⁹ / ₁₆	BENDS
eller Shaft		8066	✓	1447	✓	✓	T 32'5	29'5	180"	
"	"	"	✓	"	✓	✓	B 31'5	33'0	"	
mediate Shaft		8056	✓	1448	✓	✓	T 31'8	31'0	"	
"	"	"	✓	"	✓	✓	B 30'0.	33'0	"	
mediate Shaft		8057	✓	1473	✓	✓	T 31'2	35'0	"	
"	"	"	✓	"	✓	✓	B 31'7	31'5	"	
mediate Shaft		8058	✓	1501	✓	✓	T 30'5	30'0	"	
"	"	"	✓	"	✓	✓	B 29'0	29'0	"	
mediate Shaft		8059	✓	1494	✓	✓	T 30'7	32'5	"	
"	"	"	✓	"	✓	✓	B 30'5	31'0	"	

W G Hume



23 MAY 1921



© 2020

Lloyd's Register
Foundation

W1350-0018