

For the information of Surveyors and the Committee only.

Received at

Office.

Lloyd's Register of Shipping.

(Report on Machinery, No. 1900 Port Barrow)

No. 4315 ENGINE FORGINGS OR CASTINGS.

I have to report that the ~~Iron~~ Steel Forgings or ~~Castings~~, as herein described, manufactured by Messrs Vickers Ltd of Sheffield for the Engines No. 572 being constructed by Messrs Vickers Ltd of Barrow in Furness for the Ship No. _____, being built by _____ of _____ have been inspected by me as set forth below, and found to be, so far as can be seen, Satisfactory

Forgings or Castings.

W G Hume

Sheffield 24/11/19

Lloyd's

No.




2. Pinion Shafts

	GRANK SHAFT.		STRAIGHT SHAFTING.		
			THRUST SHAFT.	INTERMEDIATE SHAFTS.	PROPELLER SHAFT.
Material	Nickel Steel				
Condition	Forged				
Standard	Rough Machined				
Test—	Jest No 8177.		Jest No 8178.		
Yield	L 43'0.	YIELD. 28'0	L 43'0	YIELD. 28'5	
Test—	X 42'8	28'5	X 43'0	29'0.	
Per square inch	L 25'5		L 25'5		
on per cent	X 21'0		X 21'0		
ending Test—	180°		180°		
before fracture					
When Inspected	17/10/19		14/11/19		

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Machined & finished.

John Houston.



© 2020

Lloyd's Register Foundation

(if any chargeable) £

To be paid at

of iron, state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.

W1350-0019