


Lloyd's Register of Shipping.

Surveyors' Office, ANTWERP.

I hereby certify, that Albert Davé the undersigned surveyor to this society tested in
3/4 of Fabrique de Fer de Hauberg of Louvain
Boilersteel Plates specified hereunder, ordered
Messrs. Velliet & Lescaire of Amiens
 the ship No. _____ Boiler No. _____ and that the results of tests were as are set forth below.

Dimensions.			Intended for	Sample number	Charge number	Tensile tenacity			Elongation in 200 mm. in %.	Bending tests		Remarks.
Length.	Breadth.	Thick-ness.				As per rules.	Ord-ered.	By test.		Cold.	Tem-pered.	
1450 dia		15		1	423	28/32	28/32	28.8	21.5	180°	180°	
4000	1600	11		2	"	"	"	29.7	25°	"	"	
4660	1300	10		3	"	"	"	28.0	25°	"	"	
"	"	"		4	"	"	"	28.1	25°	"	"	
1650 dia.		15		5	"	"	"	"	21.5	"	"	

10/5/25
 Signed Albert Davé
 LLOYD'S REGISTER
 OF SHIPPING
 SURVEYORS' OFFICE
 ANTWERP



This Certificate is issued upon the terms of the Rules and Regulations of the Society, which provide that:—

"While the Committee use their best endeavours to ensure that the functions of the Society are properly executed, it is to be understood that neither the Committee nor the Society are under any circumstances whatever to be held responsible for any inaccuracy in any report or certificate issued by the Society or its Surveyors, or in any entry in the Register Book or other publication of the Society, or for any error of judgment, default, or negligence of the Surveyors, or other Officers or Agents of the Society."

3.—Material with less than 2½ Tons tensile strength may not be used in the construction of boilers for classed vessels, unless specially sanctioned by the Committee.

1 Ton per square inch = 1,574 Kilo per square millimeter. 1 Kilo per square millimeter = 0.635 Tons per square inch.

W1355-0026