

damage cases where the Surveyor has not made a special report he is required to state whether he offered his services for this purpose and to whom and why they were declined *not required*

Society's Freeboard maintained on Ship and

NAME "SUND"

Report *Hamburg* No.

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in *M.M.* of *AN* Iron.

PLACE.	AMIDSHIP.				FORWARD.				AFT.				REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.	Original Thickness.	Thickness by drilling.		Diminution if any.	Original Thickness.	Thickness by drilling.		Diminution if any.	
		Port.	Std.			Port.	Std.			Port.	Std.		
DECK STRAKE													
PORT STRAKE													
STARBOARD STRAKE													
Below	13	13	13		7	10	10		7	7	7		
"	8	8	8		7	10	12		7	7	7		
"	8	8	8		7	10	12		7	7½	7½		
"	8	8	8		7	8	10		7	7½	7		
"	8	8	8		7	7½	10		7	7	7		
<i>Keel plate</i>	11	11	11		10	10	10		10	10	10		
"													
"													
"													

Drillings at ends to be made in the vicinity of the peak bulkheads.

© 2020



Lloyd's Register
Foundation

W 358-0163

Breasthooks	Content of Asphalts (State which.)	Cargo Hatchways
	Rudder	Hatches
		Planking of Wood Vessels