

NAME S.S. "WESTPOOL"

Report Baltimore No. 7348

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

decimals

The thicknesses are in / of an inch.

PLATE.	AMIDSHIP.						FORWARD.						AFT.						REMARKS.
	Original Thickness.		Thickness by drilling.		Diminution if any.		Original Thickness.		Thickness by drilling.		Diminution if any.		Original Thickness.		Thickness by drilling.		Diminution if any.		
	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	
N																			
BEER STRAKE...	.66	.66	.66	-	-														
M	.62	.63	.63	-	-														
L	.62	.63	.63	-	-	.46	.50	.53	-	-	.46	.53	.53	-	-				
K	.62	.66	.59	-	.03	.46	.50	.50	-	-	.46	.56	.50	-	-				
J	.62	.56	.49	.06	.13	.46	.50	.47	-	-	.46	.66	.53	-	-				
H	.62	.53	.49	.09	.13	.46	.41	.50	.05	-	.46	.47	.53	-	-				
G	.62	.59	.49	.03	.13	.46	.41	.38	.05	.08	.46	.50	.53	-	-				
F	.62	.56	.53	.06	.09	.46	.50	.41	-	.05	.46	.47	.37	-	-				
E	.60	.50	.59	.10	.01	.46	.38	.38	.08	.08	Stealer								
D						.46	.47	.41	-	.05	.46	.59	.53	-	-				
C						.46	.59	.53	-	-	.46	.44	.38	.02	.08				
B											.46	.44	.38	.02	.08				
A											.46	.66	.50	-	-				

Drillings at ends to be made in the vicinity of the peak bulkheads.

se Frames

rudinals

Good

cient ?

Yes

Planing

W136-0026

© 2021 Lloyd's Register Foundation