

# Lloyd's Register of Shipping.

## RESULTS OF TESTS OF STEEL.

Made by Messrs STABILIMENTI DI DALMINE - Dalmine -

For Messrs Società An. FIAT- Stabilimento Grandi Motori - Turin -

Test.	Batch No.	Test No.	Charge Mark.	Thickness. (on machined test pieces).	Breadth.	Area.	Total, Tons.	Kgs. Tons per square inch. /m/m.	Extension in 8 ins. %
77	61/1	22	5766	6.7	35.5	237	11.4	48.2	24.7
		27	5766	6.6	35.5	234	11.4	48.5	25.3
		28	5766	6.7	35	237	11.7	49.3	25.4

GENOA, June 30th, 1927

(Sgd) A.S. Mantelli . -

Surveyor to Lloyd's Register



© 2021

Lloyd's Register Foundation

W48-0113