


APPLEBY-FRODINGHAM STEEL CO., LTD.,
SCUNTHORPE, Lincs.

FW Date 13th October, 1938.

Charge Test Certificate.



For Open Hearth Steel Plates.

Supplied to Messrs. Richards (Leicester) Ltd., Phoenix Works,
Leicester.

Order No.	Section	Charge	Breaking Stress (Tons) per sq. in.	Elongation % on 8 inches
496	3/8	47893	- 29.5	30.0
"	1/2	47921	- 29.8	26.0
"	7/8	47861	- 29.9	24.0
<p>Bend Tests Satisfactory.</p> <p style="color: red; font-size: 2em; font-weight: bold;">55749</p>				

For APPLEBY-FRODINGHAM STEEL CO., LTD.,



ALL STEEL SUPPLIED BY US IS OF BRITISH MANUFACTURE THROUGHOUT.



TEST HOUSE MANAGER

Lloyd's Register
Foundation

W174-0144