

AUG 9 1937

Received at \_\_\_\_\_ Office, \_\_\_\_\_ 10

# Lloyd's Register of Shipping.

(Report on Machinery, No. 22443 Port Hamburg)

## No. 1734 ENGINE ~~FORGINGS~~ OR CASTINGS.

I have to report that the ~~Forgings~~ Castings, as herein described, manufactured by Messrs. Nordische Stahlwerke Bach & Co. of Neuminster for the Engines No. \_\_\_\_\_ being constructed by Messrs. Howaldtswerke A.G. of Kiel for the Ship No. 756, being built by Messrs. Howaldtswerke A.G. of Kiel have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Kiel.

The words FORGINGS or CASTINGS should be struck out as may be required.

Mark on Forgings or Castings.

Lloyd's  
No. 6661  
P.K.18.6.37.

Hamburg, 30th June, 1937.

*J. A. Wright*

	<del>CRANK SHAFT</del>	<del>PISTON SHAFT</del>	<del>INTERMEDIATE SHAFT</del>	<del>TURBINE SHAFT</del>
	3 spindle guides 3 valve covers 12 branch pieces <del>WHEEL SHAFT</del>			<del>SCREW SHAFT</del>
Material* ...	O.H. steel			
How made ...	cast			
If Annealed...	yes			
Dimensions				
Weight { Forgings	<del>393</del> 393 kgs			
Weight, Castings ...				
Progress on Inspection {	unmachined			
Tests on Standard Test Pieces.	3" .798"			
Tensile Test— <del>Per sq. mm</del>	49.5 kg/mm <sup>2</sup>			
Extension per cent ...	25.3			
Cold Bending Test— Angle before fracture	120 degrees good.			
Dates when Inspected	18.6.37.			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Drop and hammering tests good.

Fee (if any chargeable)

To be paid at Hamburg

\* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.