

Lloyd's Register of Shipping.

Order: 180458.

(Report on Machinery, No.

48013

Port:

GLASGOW

No. 25366.

ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings ~~XXXXXXXXXX~~, as herein described, manufactured by Messrs. Fried. Krupp A.G. of Essen for the Engines No. 996 being constructed by Messrs. Fairfield Shipb. & Eng. Co. Ltd. of Govan for the Ship No. , being built by of have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Govan.

Mark on Forgings or Castings.

Lloyd's

No. 3149.

J.L. 19.8.27.

Düsseldorf 22nd August 1927.

J. Hogen

	CRANK SHAFT	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	1 shaft for journals			
	XXXXXXXXXXXX			SCREW SHAFT.
Material* ...	Annealed Siem. Mart. Ingot Steel	/		
How made ...	forged			
If Annealed ...	Yes			
Dimensions, Forgings				
Weight, Castings				
Progress on { Inspection }	rough turned			
Tests on Standard Test Pieces.	.798 3"			
Tensile Test— Tons per square inch	32.0			
Extension per cent	32.0			
Cold Bending Test— Angle before fracture	180 degr. good			
Dates when Inspected	19.8.27.			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £

To be paid at Düsseldorf.

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.