

Lloyd's Register of Shipping.

Order: 180458.

(Report on Machinery No. 48013

Port

GLASGOW

No. 25534.

ENGINE FORGINGS OR CASTINGS

I have to report that the Forgings ~~or castings~~, as herein described, manufactured by Messrs. Fried. Krupp A.G. of Essen

for the Engines No. 996 being constructed by Messrs. Fairfield Shipb. Eng. Co.

of Govan for the Ship No. , being built by

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to

Govan.

Mark on Forgings or Castings.

Lloyd's

No. 3281/3282.

J.L. 16.9.27.

R/L. 8L.

Düsseldorf 21st September 1927.


J. Fegen

	XXXXXXXXXX 2 webs with pin XXXXXXXXXX	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT. SCREW SHAFT.
Material* ...	Annealed Siem. Mart. Ingot Steel	/		
How made ...	forged			
If Annealed ...	Yes			
Dimensions, Forgings	18 1/2" Ø			
Weight, Castings ...				
Progress on Inspection	rough turned			
Tests on Standard Test Pieces.	.798 3"			
Tensile Test—				
Tons per square inch	31,5 29,1			
Extension per cent	32,0 32,0			
Cold Bending Test—				
Angle before fracture	180 degr. good			
Dates when Inspected	16.9.27.			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

*20 24 25
996
@*

*7.12.27
@*



Fee (if any chargeable) £

To be paid at Düsseldorf.

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.