

NAME

*5/8 "Dimitris"*

Report

*Bdx. No. 3860*

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in  $\frac{1}{20}$  of an inch.

	AMIDSHIP.				FORWARD.				AFT.				REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.	Original Thickness.	Thickness by drilling.		Diminution if any.	Original Thickness.	Thickness by drilling.		Diminution if any.	
		Port.	Std.			Port.	Std.			Port.	Std.		
RAKE .....													
RAKE .....	<i>15</i>	<i>14</i>	<i>14</i>	<i>1 1</i>	<i>10</i>	<i>10</i>	<i>10</i>	<i>- -</i>	<i>10</i>	<i>10</i>	<i>9</i>	<i>- 1</i>	
.....	<i>14</i>	<i>13</i>	<i>13</i>	<i>1 1</i>	<i>9</i>	<i>8</i>	<i>8</i>	<i>1 1</i>	<i>9</i>	<i>8</i>	<i>8</i>	<i>1 1</i>	
.....	<i>12</i>	<i>11</i>	<i>11</i>	<i>1 1</i>	<i>9</i>	<i>9</i>	<i>9</i>	<i>- -</i>	<i>9</i>	<i>9</i>	<i>8</i>	<i>- 1</i>	
.....	<i>12</i>	<i>11</i>	<i>11</i>	<i>1 1</i>	<i>9</i>	<i>8</i>	<i>9</i>	<i>1 -</i>	<i>9</i>	<i>8</i>	<i>8</i>	<i>1 1</i>	
.....	<i>12</i>	<i>11</i>	<i>11</i>	<i>1 1</i>	<i>9</i>	<i>9</i>	<i>8</i>	<i>1 -</i>	<i>9</i>	<i>8</i>	<i>9</i>	<i>1 -</i>	
.....	<i>12</i>	<i>11</i>	<i>11</i>	<i>1 1</i>	<i>9</i>	<i>8</i>	<i>8</i>	<i>1 1</i>	<i>9</i>	<i>8</i>	<i>9</i>	<i>1 -</i>	

Drillings at ends to be made in the vicinity of the peak bulkheads.

© 2021  
*F. Mallet*  
 Lloyd's Register  
 Foundation

W232-0053