

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office, 1 AUG 1933

# Lloyd's Register of Shipping.

(Report on Machinery, No. 7842 Port Indi.)

## No. F3577 ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings or Castings, as herein described, manufactured by Messrs Metropolitan Vickers Electrical Co. Ltd of Manchester for the Engines No. 3080 being constructed by Metropolitan Vickers Elec. Co. Ltd of S.S. City of Venice for the Ship No. \_\_\_\_\_, being built by \_\_\_\_\_ of \_\_\_\_\_

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to \_\_\_\_\_

Forgings or Castings.

Lloyd's  
No. ME633  
7-23 AS

W. A. Smith  
Manchester, 21-7-33.

	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	<u>Turbine Spindle</u>			
	<del>FLYWHEEL SHAFT.</del>			<del>SCREW SHAFT.</del>
...	<u>Q. P. forged steel</u>			
...	<u>Forged</u>			
...	<u>Yes</u>			
Forgings	<u>✓</u>			
Castings	<u>✓</u>			
on {	<u>Finished</u>			
tion {				
Standard Pieces.				
est—	<u>34.8</u>			
square inch				
per cent 2'	<u>32</u>			
ing Test—	<u>180°</u>			
fore fracture				
in Inspected	<u>2-6-33 to 11-4-33</u>			


PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

See 35 Lons. minimum. 25% elongation.

any chargeable) £ \_\_\_\_\_

To be paid at \_\_\_\_\_

wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



© 2020

Lloyd's Register  
Foundation

W236-0077