

For the information of Surveyors and the Committee only.

Received at

Office, 19 JUL 1934

Lloyd's Register of Shipping.

(Report on Machinery, No. 5084 Port Moh)

No. F3818 ENGINE FORGINGS OR CASTINGS.

I have to report that the ~~Forgings or Castings~~, as herein described, manufactured by Messrs Mitchell Shadlock & Co Ltd of Manchester for the Engines No. 3143 being constructed by Messrs Russell, Newby & Co of Altrincham for the Ship No. _____, being built by _____ of _____

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Altrincham

George Anderson & Co. Ltd.
Manchester

Forgings or Castings.

July 16, 23
Lloyd's £
No. 4187
of 28-2-34


| | CRANK SHAFT. ONE: 3 THROW N° 4187 FLYWHEEL SHAFT. | THRUST SHAFT. | INTERMEDIATE SHAFT. | TUBE SHAFT. SCREW SHAFT. |
|----------------------|--|---------------|---------------------|-----------------------------|
| Material | O.H. Eng & Steel | | | |
| Temper | Tempered | | | |
| Yield | Yes | | | |
| Size | 2 1/8 dia Run & journal | | | |
| Finish | Turned metal | | | |
| Standard Pieces. | | | | |
| Weight—square inch | 38.6 | | | |
| Strength per cent | 23.2 | | | |
| Winding Test— | 24.0 | | | |
| Time before fracture | 180° w. f | | | |
| Date Inspected | 31-1-34 to 28-2-34 | | | |

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(any chargeable) £

To be paid at

wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



© 2019

Lloyd's Register
Education

(any chargeable) £

To be paid at

wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.