




Telescopic gauge reading of furnaces.

Port Aft Boiler

L.H. Furnace.					Centre Furnace.					R.H. Furnace.				
no of corr.	A	B	C	D	no of corr.	A	B	C	D	no of corr.	A	B	C	D
1	36 ¹ / ₂	36 ¹ / ₂	36 ¹ / ₂	36 ¹ / ₄	1	37	37	37	37	1	36 ¹ / ₂	36 ¹ / ₂	36 ¹ / ₂	36 ³ / ₈
2	36 ¹ / ₂	36 ¹ / ₂	36 ¹ / ₂	36 ¹ / ₂	2	36 ¹ / ₈	37 ¹ / ₈	37 ¹ / ₈	37	2	36 ¹ / ₂	36 ¹ / ₂	36 ¹ / ₂	36 ¹ / ₂
3	36	36 ³ / ₄	36 ³ / ₄	36 ¹ / ₂	3	36 ¹ / ₂	37	37 ¹ / ₂	37	3	36	36 ¹ / ₂	36 ³ / ₄	36 ³ / ₄
4	35 ³ / ₄	36 ³ / ₄	36 ¹ / ₈	36 ¹ / ₂	4	36 ¹ / ₄	36 ⁷ / ₈	37	37	4	35 ⁷ / ₈	36 ³ / ₈	36 ³ / ₄	36 ⁷ / ₈
5	36	36	37	36 ¹ / ₂	5	36	36 ³ / ₄	37	37	5	35 ³ / ₄	36 ¹ / ₂	36 ⁷ / ₈	37
6	36 ¹ / ₂	37	37	36 ⁵ / ₈	6	36 ¹ / ₄	36 ⁵ / ₈	37	37	6	36 ¹ / ₈	36 ¹ / ₂	37	37
7	36 ¹ / ₂	37	37	36 ⁵ / ₈	7	36 ¹ / ₂	36 ⁵ / ₈	36 ³ / ₄	37	7	36 ¹ / ₂	36 ⁵ / ₈	37 ¹ / ₈	37 ¹ / ₄
8	36 ¹ / ₄	37 ¹ / ₈	37	36 ³ / ₄	8	37	36 ¹ / ₂	36 ⁵ / ₈	36 ³ / ₄	8	36 ³ / ₄	37	37 ¹ / ₄	37 ¹ / ₄
					9	37	36 ¹ / ₄	36 ³ / ₈	36 ⁵ / ₈					



Remarks:- Internally:- Furnaces pitted and corroded on top half more pronounced above fire line.

Externally:- Very rough.

Starboard Aft Boiler

Centre Furnace.				
no of corr.	A	B	C	D
1	37	37	36 ³ / ₄	36 ⁷ / ₈
2	37	37	36 ¹ / ₂	36 ³ / ₄
3	37	37	36 ¹ / ₄	36 ³ / ₄
4	36 ³ / ₄	36 ³ / ₄	36 ¹ / ₄	36 ³ / ₄
5	36 ³ / ₄	36 ⁵ / ₈	36	36 ³ / ₄
6	36 ⁵ / ₈	36 ¹ / ₂	36	36 ⁵ / ₈
7	36 ¹ / ₂	36 ¹ / ₂	35 ³ / ₄	36 ¹ / ₂
8	36 ⁵ / ₈	36 ¹ / ₂	35 ³ / ₄	36 ¹ / ₂
9	36 ³ / ₄	36 ¹ / ₄	35 ³ / ₄	36 ¹ / ₈

