

# Lloyd's Register of Shipping.

(Report on Machinery, No. \_\_\_\_\_ Port ANTWERP)

## No. 5124 ENGINE ~~FORGINGS OR~~ CASTINGS.

I have to report that the ~~Forgings or~~ Castings, as herein described, manufactured by The Acieries de Namie St Pierre of Namie St Pierre for the Engines No. \_\_\_\_\_ being constructed by The Mercantile Marine Coy of Antwerp for the Ship LEOPOLDVILLE No. \_\_\_\_\_, being built by \_\_\_\_\_ of \_\_\_\_\_

have been inspected by us as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to The Mercantile Marine Coy.

The words FORGINGS or CASTINGS should be struck out as may be required.

Mark on Forgings or Castings.

Lloyd's  
No. 5124  
R.L. 25.9.36  
W.H. 14.10.36

A. Lassalle. & Herbert Hatt.  
Antwerp

	CRANK SHAFT.  FLYWHEEL SHAFT.	THRUST SHAFT. 110 VALVE CASINGS, COVERS ETC.	INTERMEDIATE SHAFT.	TUBE SHAFT.  SCREW SHAFT.
Material* ...	/	O.N. Steel	/	/
How made ...		Cast.		
If Annealed ...		Annealed.		
Dimensions, Forgings				
Weight, Castings ...		3033 Kilos.		
Progress on { Inspection }		Rough.		
Tests on Standard Test Pieces.				
Tensile Test— Kilos Tons per square inch		50.5    51.8		
Extension per cent		25    27		
Cold Bending Test— Angle before fracture		120°    120° WF 4.9.36. 11.9.36 18.9.36		
Dates when Inspected	25.9.36 14.10.36			


PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Hammering Tests satisfactory.

Fee (if any chargeable) £ \_\_\_\_\_

To be paid at \_\_\_\_\_

\* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



© 2019

Lloyd's Register  
Foundation

W251-0116