

# Lloyd's Register of Shipping.

(Report on Machinery, No. \_\_\_\_\_ Port ANTWERP)

No. 6077 ENGINE ~~FORGINGS OR~~ CASTINGS.

I have to report that the ~~Forgings or Castings~~, as herein described, manufactured by The Acieries de Haine St Pierre of Haine St Pierre for the Engines No. \_\_\_\_\_ being constructed by The Mercantile Marine of Antwerp for the Ship No. LEOPOLDVILLE, being built by \_\_\_\_\_ of \_\_\_\_\_

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to The Mercantile Marine, Antwerp.

The words FORGINGS or CASTINGS should be struck out if may be required.

Mark on Forgings or Castings.

Lloyd's  
No. 6077  
R. W. H.

W. Herbert Hatt.

Antwerp, 11.12.36.

	CRANK SHAFT.  FLYWHEEL SHAFT.	THRUST SHAFT. 10 TEE PIECES.	INTERMEDIATE SHAFT.	TUBE SHAFT.  SCREW SHAFT.
Material* ...		<u>O.H. Steel.</u>		
How made ...		<u>Cast.</u>		
If Annealed ...		<u>Annealed.</u>		
Dimensions, Forgings				
Weight, Castings ...		<u>341 Kilo.</u>		
Progress on } Inspection }		<u>Rough.</u>		
Tests on Standard Test Pieces.				
Tensile Test— <u>Kilograms per square inch</u>		<u>53.4</u>		
Extension per cent		<u>28.0</u>		
Cold Bending Test— Angle before fracture		<u>120° W.F.</u>		
Dates when Inspected		<u>8:12:36.</u>		

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Hammering Tests satisfactory.

Fee (if any chargeable) £ \_\_\_\_\_

To be paid at \_\_\_\_\_

\* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

