

Cepolduit

For the information of Surveyors and the Committee only.

Received at _____ Office, _____ 19__

Lloyd's Register of Shipping.

(Report on Machinery, No. _____ Port _____)

No. 2198 ENGINE ~~FORGINGS OR~~ CASTINGS.

I have to report that the ~~Forgings or~~ Castings, as herein described, manufactured by Acieries de Hamme-St-Pierre et Lesquin of Hamme-St-Pierre for the ~~Engines~~ Nos. ^{Order} 5323, 8554 & 9080 being constructed by Mercantile Marine & G. D Co. of Antwerp for the Ship No. ✓, being built by _____ of _____

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Antwerp.

The words FORGINGS or CASTINGS should be struck out as may be required.

Mark on Forgings or Castings.

Lloyd's
No. 2198
FR. 2/12/36

J. Robertson

Antwerp

3/12/36.

	CRANK SHAFT. <u>2 Corps de Soupapes</u> FLYWHEEL SHAFT.	THRUST SHAFT. <u>2 Soupapes</u> <u>2 Coumercles</u>	INTERMEDIATE SHAFT. <u>2-T Pieces</u>	TUBE SHAFT. <u>1-T Piece</u> SCREW SHAFT <i>(replace)</i>
Material* ...	<u>S. M. S. S. Steel</u>			
How made ...	<u>Cast</u>	<u>Cast</u>	<u>Cast</u>	<u>Cast</u>
If Annealed...	<u>Annealed</u>	<u>Annealed</u>	<u>Annealed</u>	<u>Annealed</u>
Dimensions } Weight } Forgings	<u>✓</u>	<u>✓</u>	<u>✓</u>	<u>✓</u>
Weight, Castings ...	<u>88 Kgs</u>	<u>28.1 Kgs</u>	<u>65.7 Kgs</u>	<u>53 Kgs</u>
Progress on Inspection	<u>Rough Castings</u>			
Tests on Standard Test Pieces.	_____			
Tensile Test— <u>Kgs Tons per square inch</u>	<u>54.7</u>		<u>51.5</u>	
Extension per cent	<u>27</u>		<u>30</u>	
Cold Bending Test— Angle before fracture	<u>120°</u>		<u>120°</u>	
Dates when Inspected	<u>2/12/36</u>		<u>2/12/36.</u>	

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Hammered.



© 2019

Lloyd's Register
Foundation

Fee (if any chargeable)

To be paid at

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.