

Lloyd's Register of Shipping.

(Report on Machinery, No. _____)

Port ANTWERPNo. 6017 ENGINE ~~FORGINGS OR~~ CASTINGS.

I have to report that the ~~Forgings or~~ Castings, as herein described, manufactured by The Acieries de Namur St Pierre of Namur St Pierre for the Engines No. _____ being constructed by The Mercantile Marine Co of Antwerp for the Ship NOLEBOLDVILLE being built by _____ of _____

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to The Mercantile Marine Co. Antwerp

Mark on ~~Forgings or~~ Castings.

Lloyd's

No. 6017WH. 20.11.36W Herbert NottAntwerp28.11.36

	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	FLYWHEEL SHAFT.	2 VALVE CASINGS 2 VALVE COVERS.		SCREW SHAFT.
Material* ...		<u>O.H. Steel.</u>		
How made ...		<u>Cast.</u>		
If Annealed ...		<u>Annealed.</u>		
Dimensions, Forgings				
Weight, Castings ...		<u>1,418 Kilos.</u>		
Progress on { Inspection }		<u>Rough.</u>		
Tests on Standard Test Pieces.				
Tensile Test— Kilos Tons per square inch		<u>54.1</u> <u>53.5</u>		
Extension per cent ...		<u>28</u> <u>30</u>		
Cold Bending Test— Angle before fracture ...		<u>120°</u> <u>120° W.F.</u>		
Dates when Inspected		<u>20.11.36</u>		

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Hammering Tests satisfactory.

Fee (if any chargeable) £

To be paid at

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.