

SSEL'S NAME

S/S. IZ RADA

Report

TRIESTE

No. 6690

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in  $\frac{1}{20}$  of an inch.

STRAKE.	AMIDSHIP.						FORWARD.						AFT.						REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.					
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.				
R SHEER STRAKE	O	22	22	22	-	-	14	14	14	-	-	13	13	13	-	-			
ake below	N	22	21	21	1	1	14	14	14	-	-	13	12	13	1	-			
EN SHEER STRAKE	M	22/23	24	23	-	-	22	21	21	1	1	22	22	23	-	-			
Strake below	L	27	26	26	1	1	18	19	19	-	-	18	20	20	-	-	PLEASE SEE SKETCH IN FIRST ENTRY REP.		
"	K	27	26	25	1	2	18	22	22	-	-	18	20	20	-	-			
"	J	27	26	26	1	1	18	21	21	-	-	18	20	20	-	-			
"	I	27	26	25	1	2	18	20	20	-	-	18	21	21	-	-			
"	H	27	26	26	1	1	18	20	20	-	-	18	20	20	-	-			
"	G	27	28	28	-	-	18	20	21	-	-	18	20	20	-	-			
"	F	27	Cent	Cent	-	-	18	21	21	-	-	18	21	21	-	-			
"	E	27	Cent	Cent	-	-	18	Cent	Cent	-	-	18	21	19	-	-			
"	D	27	Cent	Cent	-	-	18	Cent	Cent	-	-	18	20	20	-	-			

Drillings at ends to be made in the vicinity of the peak bulkheads.

To the Surveyors,

Effence Vidukey

Lloyd's Register  
Foundation

7610-852M