

S. NAME S. S. "SVAVA" Report Copenhagen No. 8234

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in  $20^{\text{ths}}$  of an inch.

PLATE	AMIDSHIP.						FORWARD.						AFT.						REMARKS.	
	Original Thickness.		Thickness by drilling.		Diminution if any.		Original Thickness.		Thickness by drilling.		Diminution if any.		Original Thickness.		Thickness by drilling.		Diminution if any.			
	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.		
DECK ABOVE STRAKE	6	6	6																	Midship drillings taken in way of Bunkers. End drillings taken in the vicinity of the peak bulkheads.
DECK ABOVE SHEER	6	6	6																	
DECK STRAKE	12	19 $\frac{1}{2}$	20	12	1	9	9	9	9	9										
DECK LOW	9	8	8	1	1	8	9	9	8	8	8	8	8	8	8	8	8	8		
	10	10	9		1	8	8	9	8	7	7									
	9	9	9			8	8	8	8	5	7 $\frac{1}{2}$									
	11	10	10	1	1	9	9	10	9	7	7 $\frac{1}{2}$								Sheer strake doubled for $\frac{1}{2}$ length, full breadth doubling $9/20$ ".	
						9	10	9	9	7 $\frac{1}{2}$	7									

Copenhagen 5<sup>th</sup> May 1930.

J.R. Macleod

Drillings at ends to be made in the vicinity of the peak bulkheads.

Lloyd's Register Foundation

W263-0017