

Nr.

943

Fortsetzung

1

Blanket Nr. 98 B.

Das Material ist bestimmt für:	Stempelung des Materials:	Charge	Probestück:				Bruchbelastung:		Dehnung:		Resultate der Biegeproben:	Bemerkungen *)
			Stempel:	Breite: mm.	Dicke: mm.	Querschnitt: qmm.	Total in 1000 kg.	Kg. pro qmm.	Mess- länge: mm.	%		
Signo G	AV	6981	340	34.-	19.4	660	38.5	43.2	200	32.-	gut	
"	"	"	340	34.-	19.4	660	38.9	43.7	"	28.-	"	→
"	"	"	341	34.-	19.4	660	39.3	44.3	"	30.5	"	
"	"	"	341	34.-	19.4	660	39.9	45.3	"	30.-	"	→
"	"	"	342	34.-	19.4	660	30.6	46.3	"	26.5	"	
"	"	"	342	34.-	19.4	660	31.-	46.9	"	24.5	"	→
"	J	6921	343	30.3	21.2	642	37.6	42.9	"	28.5	"	
"	"	"	343	30.3	21.2	640	38.9	45.2	"	28.-	"	→
"	K	6981	344	30.2	21.4	646	39.4	45.5	"	27.-	"	
"	"	"	344	30.2	21.4	646	30.-	46.4	"	28.-	"	→
"	L	"	345	30.1	22.-	662	38.6	43.2	"	29.-	"	
"	"	"	345	30.1	22.-	662	39.2	44.-	"	29.-	"	→
"	M	6845	346	18.7	36.-	673	33.5	49.7	"	25.-	"	
"	"	"	346	18.7	36.-	673	33.8	50.2	"	25.-	"	→
"	"	"	347	18.7	35.5	664	35.-	52.7	"	21.-	"	
"	"	"	347	17.8	35.8	636	33.8	53.1	"	23.-	"	→
"	O	6953	348	23.8	27.4	652	32.4	49.7	"	26.5	"	
"	"	"	348	23.8	27.3	650	32.7	50.2	"	25.-	"	→
"	P	5244	349	23.8	30.-	714	35.6	49.8	"	24.5	"	
"	"	"	349	23.6	30.-	708	35.5	50.1	"	25.-	"	→
"	Q	7234	350	18.7	33.6	628	31.7	50.3	"	25.-	"	
"	"	"	350	18.7	33.8	632	32.3	51.-	"	26.-	"	→
"	R	6953	351	33.9	19.3	654	33.6	51.3	"	27.5	"	
"	"	"	351	34.-	19.4	660	34.1	51.6	"	26.-	"	→

Jeder Blech ist markiert: VIT, Charge-No., Walzstück-No., NV, AV.

Prüf., 19. II. 1937.