

For the information of Surveyors and the Committee only.

Received at

Office,

19

Lloyd's Register of Shipping.

(Report on Machinery, No.

Port

Quebec

of 1995

ENGINE FORGINGS OR CASTINGS.

I have to report that the ~~Iron or Steel Forgings or Castings~~, as herein described,

manufactured by The Darlington Forge Co. of Darlington

for the Engines No. 4 being constructed by Edgewater & Co.

for the Ship No. _____, being built by

of

have been inspected by me as set forth below, and found to be, so far as can be seen, Sound

in the order of J. H. Kentlebury Esq. London

ings or Castings.

nd's

36 1/2 D
MR

M. Robertson

Darlington 18-12-20

	CRANK SHAFT.	STRAIGHT SHAFTING		
		THRUST SHAFT.	INTERMEDIATE SHAFTS.	PROPELLER SHAFT.
	<u>S.M. Ingot Steel</u> <u>Forged</u> <u>15 3/4 dia</u>			<u>S.M. Ingot Steel</u> <u>Forged</u> <u>15 3/4 dia</u>
	<u>Forged Finished</u> <u>webs</u>	<u>webs</u>	<u>Fins</u>	<u>Forged Finished</u> <u>2 Ends of fin</u>
Standard CES.	<u>2 1/4 940-31-2</u>	<u>940A-31-6</u>	<u>860-29-4</u>	<u>1 1/4-31-6</u>
are in	<u>31-0</u>	<u>32-0</u>	<u>33-0</u>	<u>32-0</u>
cent	<u>31-0</u>	<u>32-0</u>	<u>33-0</u>	<u>32-0</u>
Test	<u>180</u>	<u>180</u>	<u>180</u>	<u>180</u>
fracture	<u>180</u>	<u>180</u>	<u>180</u>	<u>180</u>
inspected	<u>25-8-20-16-12-20</u>			<u>25-8-20-16-12-20</u>

Particulars of other tests applied to castings:-
96-32-0-29-0-180
96A-31-6-30-0

webs
2 1/4 320A-30-0
32-0
180

if any chargeable) £ 6-6-0

to be paid at Darlington

of 23.12.20

on, state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.

W280-0093

© 2020

Lloyd's Register
Foundation