

# Lloyd's Register of Shipping.

(Report on Vessel No. Port )

No. 6170 SHIP ~~FORGINGS OR~~ CASTINGS.

I have to report that the undermentioned ~~XXXXXX~~ Steel ~~Forgings~~ Castings, manufactured by W. Shaw & Co. Ltd., of Middlesbrough for the Vessel No. 951, being built by Lithgow's Ltd. of Port Glasgow, have been inspected by me as set forth below and found to be, so far as can be seen, sound and free from defects.

for - John Hastie & Co. Ltd.,

Mark on ~~XXXXXX~~ Castings.

Lloyd's  
No. 6170  
L.R. 6.11.40

1 - Quadrant

Greenock

Louis P. Poley

Middlesbrough 12.11.40

	STEEL	RUBBER	STEEL
Material*	S.M. Acid O.H. Steel		
How made	Cast		
If annealed	Yes		
Dimensions	To plan		
Progress on Inspection	Part machined		
Date when Inspected	10.10.40 - 6.11.40		
CASTINGS.			
Tests on Standard Test Pieces.			
Tensile Test—			
Ultimate Tensile.			
Tons per sq. in....	29.6		
Yield Point.	-		
Tons per sq. in....			
Extension per cent on.....inches	30.0		
Red. of Area %	-		
Cold Bending Test—			
Angle before fracture	120° WF.		
Drop Test—			
Height from ground ..	10'-0"		
Hammering Test—			
If made according to Rules and found satisfactory ...	Yes		


SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Wt 10 - 1 - 14

Fee (if any chargeable) £ : 5 : 0

To be paid at Mdb.

\* If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.



© 2020

Lloyd's Register Foundation

030-0096