

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office \_\_\_\_\_ 19

# Lloyd's Register of Shipping.

(Report on Vessel No. \_\_\_\_\_ Port \_\_\_\_\_)

No. 2812 SHIP ~~FORGINGS OR~~ CASTINGS.

I have to report that the undermentioned ~~Iron or Steel Forgings or~~ Castings, manufactured by *The Springfield Steel Co. Ltd* of *Glasgow* for the Vessel No. *363*, being built by *Messrs Camper Nicholson's Ltd* of *Southampton* have been inspected by me as set forth below and found to be, so far as can be seen, sound & free from defects.

*Casting dispatched to Messrs J. Hadie & Co. Ltd. Greenock.*

on Forgings or Castings.



Lloyd's  
No. 2812  
W.L. 21.2.29.

*1 Tiller (split box) Cap.*

|  | STERN FRAME.                                  | RUBBER FRAME. | STEM. |
|--|---|---------------|-------|
| Material*  | <i>Siemens-Martin Acid, Open Hearth Steel</i> |               |       |
| Made   | <i>Cast</i>                                   |               |       |
| Treated  | <i>Annealed</i>                               |               |       |
| Dimensions   | <i>To pattern</i>                             |               |       |
| Process on Inspection                              | <i>Rough dressed.</i>                         |               |       |
| When Inspected                                     | <i>18/2/29 - 21/2/29.</i>                     |               |       |
| CASTINGS.  | <i>Test No 8</i>                              |               |       |
| Tests on Standard Test Pieces.                     |   |               |       |
| Tensile Test—                                      | <i>32.8</i>                                   |               |       |
| Stress per square inch                             | <i>26.0%</i>                                  |               |       |
| Elongation per cent. ...                           | <i>120° W.F.</i>                              |               |       |
| Bending Test—                                      | <i>10 feet</i>                                |               |       |
| Angle before fracture                              | <i>Yes.</i>                                   |               |       |
| Test—  |   |               |       |
| Height from ground ...                             |   |               |       |
| Hardening Test—                                    |   |               |       |
| Made according to Rules and found satisfactory ... |   |               |       |

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

T. c. gr. lbs.  
- 6.2.19

Fee (if any chargeable) £NIL (Vessel Classed)

To be paid at \_\_\_\_\_

If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.

T. T.

W319-0194



© 2019

Lloyd's Register  
Foundation

*Son*

signed

*As none*

*MM*