

DATE.	OF TEST.	CONSIGNEE.	QUALITY.	TEST PIECE.			STRESS.		PERCENT. ON		TESTED BY	REMARKS.
				Breadth.	Thick- ness.	Area.	Total.	Per Sq. In.	3"	Bends		
24.5.19	9588	John. G. Kinnaird & Co	52 1/2	798	2 1/2	5	15.6	31.2	27	180°	Brit Corp.	1 Prop. Shaft
	9609	M 1/29 31/32 of 2/5/18	"	"	"	"	15.4	30.8	29	180°	" "	1 Thrust "
	9612	1/5	"	"	"	"	15.7	31.4	30	180°	" "	5 Corp. Ends
	"	6	"	"	"	"	15.6	31.2	28.0	"	" "	1 " "
	"	10/11	"	"	"	"	15.9	31.8	30	"	" "	2 " "
	"	7/8	"	"	"	"	15.5	31.0	32	"	" "	2 " "
	9613	1	"	"	"	"	15.0	30.0	29	"	" "	1 " "
	"	2	"	"	"	"	15.4	30.8	31	"	" "	1 " "
	9614	1	"	"	"	"	15.5	31.0	29	"	" "	1 Body Piece
	"	2	"	"	"	"	16.2	32.4	29	"	" "	1 " "
	9615	2	"	"	"	"	16.0	32.0	34	"	" "	1 Pin
	"	1	"	"	"	"	15.5	31.0	30	"	" "	1 "
	"	3	"	"	"	"	15.4	30.8	31	"	" "	1 "



© 2020

Lloyd's Register
Foundation

W347-0035