

CELLINA
Rpt. 8.
Com. 03190/11/7/36
22.6.37
M

For the information of Surveyors and the Committee only.

Received at

Office

NOV 16 1937

Lloyd's Register of Shipping.

(Report on Vessel No. 118975 Port TRIESTE)

No. 389

SHIP ~~FORGINGS~~ OR CASTINGS.

I have to report that the undermentioned ~~Iron or Steel Forgings or~~ Castings, manufactured by Sra. Atli Fornie Acciaierie d'Italia of Venice Marghera for the Vessel No. NLT, being ^{repaired} ~~built~~ by Cantieri Riuniti dell'Ad. of Monfalcone have been inspected by me as set forth below and found to be, so far as can be seen, sound and free from defects.

The words FORGINGS or CASTINGS, IRON or STEEL, should be struck out as may be required.

Mark on ~~Forgings or~~ Castings.

Lloyd's
No. 1158
M B 23.11.36

Trieste 26th November 1936.


Gov. Spennett
Support

	STERN FRAME.	RUDDER FRAME.	STEM.	
Material* ...	/	<u>S. M. steel</u>	/	
How made ...		<u>cast</u>		
If annealed ...		<u>yes</u>		
Dimensions ...		<u>to drawing</u>		
Progress on Inspection ...		<u>rough machined</u>		
Date when Inspected ...		<u>17.20/10 * 23/11/36</u>		
CASTINGS.				
Tests on Standard Test Pieces.				
Tensile Test— <u>Rg</u> Tens per square inch ^{mm²} ...		<u>49</u> <u>25.2</u>		
Extension per cent. ...				
Cold Bending Test— Angle before fracture ...	<u>180° good</u>			
Drop Test— Height from ground ...				
Hammering Test— If made according to Rules and found satisfactory ...	<u>Yes</u>			

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Fee (if any chargeable) £

To be paid at Trieste



© 2019

Lloyd's Register Foundation

* If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.

W38-0114