

GLASGOW REPORT No. 54400

Lloyd's Register of Shipping.

RESULTS OF TESTS OF STEEL. *Forgings*


by Messrs. D. Rowan & Co. Ltd. Glasgow. Eng No 970

The Burntisland Ship Co. Ltd. Burntisland. Ship No 180

Test Batch No.	No. of Pieces.	Description.	Charge Mark.	Sample No.	Sea Thickness.	Area.	Tons per square inch.	Extension on 3" inches.
								% Bend.
59.	2.	Crank Journals & 1. End.			.798	.50	30.1	33. 180°
60	3.	Crank Pins			"	"	31.6	30 "
61	1.	Coup End.			"	"	31.3	31.5 "
62	1.	Thrust Shaft.			"	"	31.3	31.5 "
63	1.	Prop. Shaft.			"	"	31.6	29 "
64	3	Crank Webs.			"	"	30.3	32 "
65	3	- do - do -			"	"	29.7	31.5 "
66	2.	Piston Rods			"	"	34.7	28 "
67		- do - do -			"	"	34.9	27.5 "
R 68	2.	Conn. Rods			"	"	27.1	32 "
R 69	1	- do - do -			"	"	29.0	30.5 "

Chas. S. Porter.

Glasgow. 10/3/1934



© 2019

Lloyd's Register
Foundation

The foregoing is a correct description,