

Lloyd's Register of Shipping.

RESULTS OF TESTS OF STEEL. SHAFTS.

by MESSRS. WM. BEARDMORE & CO., LTD., GLASGOW.

MESSRS. D. ROWAN & CO., LTD. ENG. NO. 958 - FOR MESSRS. LITHGOWS' SHIP NO. 863.

Batch No.	No. of Pieces.	Description.	Charge Mark.	Sample No.	Dia. Thickness.	Area.	Tons per square inch.	Extension on 3 inches.	% Bend
<u>Test No.</u>									
6814/5/6	3	Coupling Ends			1798	.50	30.6	27.5	180
6817/8/9	3	Crank Pins			"	"	31.6	31.0	"
6820	1	Crank Journal			"	"	31.6	31.0	"
6821	1	Crank End			"	"	31.6	31.0	"
6822	1	Thrust Shaft			"	"	28.0	38.0	"
6823	1	Inter. Shaft			"	"	29.6	28.0	"
6824	1	Inter. Shaft			"	"	29.2	30.0	"
6825	1	Do.			"	"	30.2	32.0	"
6826	1	Do.			"	"	29.6	30.0	"
6827	1	Do.			"	"	30.4	29.0	"
6828	1	Do.			"	"	30.8	30.0	"
6829	1	Do.			"	"	30.4	28.0	"
6830	1	Prop. Shaft			"	"	30.2	30	"
6831	1	Do.	Spare		"	"	31.8	28	"

Chas. J. Porter.

Glasgow. 6/7/1933.



© 2019

Lloyd's Register Foundation

W405-0023

(2)