

FRAMES, DOUBLE BOTTOM AND BEAMS.

VESSEL'S NAME *S/S "VALIENTE"* EX. *OBRIEN BROTHERS* Report *n. yk* No. *40295*

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

As per plans - now approved
The thicknesses are in $\frac{1}{100}$ of an inch.
See still expansion

STRAKE.	AMIDSHIP.					FORWARD.					AFT.					REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.	
BRIDGE SHEER STRAKE.....	.70															
Strake below64															
SHEER STRAKE66	.70	.56	.10	.52	.60	.65				.70	.75	.63	.07		
1st Strake below	K	.74	.70	.66	.08	.58	.60	.60			.56	.63	.63			
2nd " "	J	.66	.70	.72		.50	.47	.53	.03		.50	.63	.63			
3rd " "	H	.66	.70	.70		.52	.53	.47	.05		.54	.56	.56			
4th " "	G	.66	.70	.64	.02	.50	.53	.53			.50	.50	.50			
5th " "	F	.66	.72	.72		.52	.47	.53	.05		.46	.44	.50	.02		
6th " "	E	.66	.72	.72		.52	.53	.60			.46	.47	.53			
7th " "	D	.66	.56	.56	.10	.56	.53	.47	.03	.09	.42	.53	.60			
8th " "	C	.62	.70	.70							.48	.47	.60	.01		
9th " "	B	.62	.65	.66		.62	.65	.63								
10th " "	A	.66	.72	.56	.10	.66	.50	.50	.16	.16	.48	.38	.47	.10	.01	
KEEL	1.02	.94	.08		.72	.63	.09				.82	.78	.04			

Drillings at ends to be made in the vicinity of the peak bulkheads.

© 2020

Lloyd's Register
Foundation

W42-0040

Are the scantlings and arrangements in way of the **Bottom Forward** in accordance with the Rules and/or as approved?

bottom in E. & B. space and framing in Bunkers and Boiler Room?