

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office, \_\_\_\_\_ 19

JUL 1929

# Lloyd's Register of Shipping.

(Report on Machinery, No. 40337 Port Hull.)

## No. 18233 ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings or Castings, as herein described, manufactured by The Rotherham Forge & R. Mills Ltd of Rotherham for the Engines No. 593 being constructed by Messrs Amos & Smith Ltd. of Hull for the Ship No. \_\_\_\_\_, being built by \_\_\_\_\_ of \_\_\_\_\_

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to \_\_\_\_\_

Forgings or Castings.

RW Hawcett  
Sheffield  
12/7/29

Lloyd's  
No. 2 N.F. 10/7/29


	<del>CRANK SHAFT.</del>	<del>THRUST SHAFT.</del>	<del>INTERMEDIATE SHAFT.</del>	<del>TUBE SHAFT.</del>
	<u>3 Piston Rods</u>			
	<del>FLYWHEEL SHAFT.</del>			<del>SCREW SHAFT.</del>
Material	<u>Siemens Steel</u>			
Mode of Manufacture	<u>Forged</u>			
Material tested	<u>Yes</u>			
Material, Forgings	<u>-</u>			
Material, Castings	<u>-</u>			
Section	<u>Black Forgings</u>			
on Standard Test Pieces.	<u>865</u>			
Test—per square inch	<u>36.4</u>			
Extension per cent	<u>28.0</u>			
ending Test—before fracture	<u>180°</u>			
When Inspected	<u>2/7/29 to 10/7/29</u>			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(if any chargeable) £

To be paid at

If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



© 2019

Lloyd's Register Foundation

W434-0018

W434-0021