

7.

For the information of Surveyors and the Committee only.

Received at

Office,

19

# Lloyd's Register of Shipping.

Nom. 783358

(Report on Machinery, No.

Port

No. 388

## ENGINE FORGINGS OR CASTINGS.

I have to report that the ~~Iron or Steel Forgings or Castings~~, as herein described, manufactured by *Messrs. Skoda Ltd.* of *Pilsen, Bohemia* for the Engines No. *374/7* being constructed by *Messrs. A. P. Götawerken & Co* of *Göteborg* for the Ship No. , being built by of

have been inspected by me as set forth below, and found to be, so far as can be seen, *sound and free from defects.*

*Two (2) three throw crankshafts, complete and bolted together.*

Forgings or Castings.

Lloyd's

No. 1325

RH 1.24

*Prague 19<sup>th</sup> February 1924*  
*C. E. Hughes.*

	2 CRANK SHAFT.3	STRAIGHT SHAFTING.		
		THRUST SHAFT.	INTERMEDIATE SHAFTS.	PROPELLER SHAFT.
1* ...	<i>Annealed S. M. S. Steel</i>			
ade ...	<i>Forged &amp; Built</i>			
ons ...	<i>14 3/8" &amp; (365 mm)</i>			
s on { ction }	<i>Finished Condition</i>			
on Standard t Pieces.	<i>Pins</i>	<i>Webs</i>	<i>Shaft Journals</i>	
Test— er square inch	<i>47.9 - 48.4 : 47.7 - 51.6 - 50.4 - 48.2 - 47.6 - 50.7 - 48.5 : 48.9 - 47.4 - 48.5</i>			
ion per cent	<i>31.6 - 34.2 : 33.6 - 32.3 - 31.6 - 32.3 - 29.0 - 31.6 - 32.9 : 31.6 - 31.6 - 32.9</i>			
nding Test— before fracture	<i>180°</i>	<i>180°</i>		<i>180°</i>
hen Inspected	<i>30. 1. 1924</i>	<i>30. 1. 1924</i>		<i>30. 1. 1924</i>

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

e (if any chargeable) £

To be paid at

*Prague.*

of iron, state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.

W434-0136

© 2019

Lloyd's Register  
Foundation