

7. For the information of Surveyors and the Committee only.

Received at Office, 19

Lloyd's Register of Shipping.

(Report on Machinery, No. 7540 Port LA)

No. 62 ENGINE FORGINGS OR CASTINGS.

I have to report that the ~~Iron or Steel Forgings or Castings~~, as herein described, manufactured by Bethlehem Steel Corpn., of Los Angeles, Calif., M.S. "SVEABORG" repaired for the ~~Engines No.~~ being constructed by Bethlehem SB. Corporation, of San Francisco, Calif., for the Ship No. , being built by of

have been inspected by me as set forth below, and found to be, so far as can be seen, good and sound.

Forgings or Castings.

Rank Web
Lloyd's
No. 62
GA 18-2-36

Coupling Journal
LLOYDS
No. 62-A
F.G.A. 18-2-36

F. B. Archbold

LOS ANGELES, CALIF.

	CRANK Web SHAFT.	STRAIGHT SHAFTING.		
		THRUST SHAFT.	INTERMEDIATE SHAFTS.	PROPELLER SHAFT.
	Steel	Steel	Crank Pin Steel	Crank Pin Steel
	Forged	Forged	Forged	Forged
	As per plan	As per plan	As per plan	As per plan
	Rough turned	Rough turned	Rough turned	Rough turned
on Standard t Pieces.		✓	✓	
Test— er square inch	70920	69600	70800	67430
ion per cent	26.7	30%	29.6	26
nding Test— before fracture	180°	180°	180°	180°
hen Inspected	Feb. 3, 1936 18-2-36	3-2-36 18-2-36	3-2-36 18-2-36	3-2-36 18-2-36

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

ANK PIN
LOYDS
2-B
18-2-36

CRANK PIN
LLOYDS
62-C
F.G.A. 18-2-36

(if any chargeable) £
To be paid at Paid at Los Angeles

of iron, state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.