

Lloyd's Register of Shipping.

Order: 2336.71.

(Report on Machinery, No. 9638

Port 970

No. 28913 ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings ~~as castings~~, as herein described, manufactured by Messrs. Henschel & Sohn A.G. of Hattingen for the Engines No. _____ being constructed by Messrs. Kockums mek. Verkstad A.B. of Malmö for the Ship No. "BODEN", being built by _____ of _____

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Malmö.

Mark on Forgings or Castings.

Lloyd's

No. 3474.

Düsseldorf 12th August 1929.

A.S. 25-10-29.

L. J. J. J.

	CHUNKY 1 coupling shaft CHUNKY	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
				SCREW SHAFT.
Material* ...	Annealed Sien. Mart. Ingot Steel			
How made ...	forged			
If Annealed...	Yes			
Dimensions, Forgings	300 mm Ø			
Weight, Castings				
Progress on { Inspection }	rough turned	Examined finished at Malmö.		
Tests on Standard Test Pieces.	.798 3"	Admiral		
Tensile Test— Tons per square inch	33.0			
Extension per cent	27.6			
Cold Bending Test— Angle before fracture	180 degr. good			
Dates when Inspected	10.8.29.			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

The material has been ordered to special requirements.

Fee (if any chargeable) £

To be paid at Düsseldorf.

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

Order: 3350.71

XXXXXX as herein described, manufactured

Meßner, Hansschel & Sohn A.G.
Hattlingen

Measures. Kockums med. Verkstad A.B.

Om Loh

Özlem

Düsseldorf 18th August 1829.


3474

PS-01-PS.2.4 XEROX/BIOL/XX

[illegible]

The material has been ordered to special requirements.

It's the point of Masselosort.



19-8-29
Surveyors Office