

Lloyd's Register of Shipping.

Order: 264.74.

(Report on Machinery, No. 9638)

Port

Malmö

No. 28851. ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings ~~or Castings~~, as herein described, manufactured by Messrs. Henschel & Sohn A.G. of Hattingen for the Engines No. being constructed by Messrs. Kockums mek. Verkstad A.B. of Malmö for the Ship No. "BODEN", being built by

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Malmö.

Mark on Forgings or Castings.

Lloyd's

No. 3407.

V.S. 22.7.29.

Düsseldorf 23rd July 1929.

K. Thorne

	CRANK SHAFT	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	1 valve ring			SCREW SHAFT.
Material* ...	Annealed Siem. Mart. rolled Ingot Steel			
How made ...	rolled			
If Annealed ...	Yes			
Dimensions, Forgings	1420x76			
Weight, Castings				
Progress on { Inspection }	rough turned	Examined finished at Malmö.		
Tests on Standard Test Pieces.	.798 8xd	Adm. in		
Tensile Test— Tons per square inch	35.2			
Extension per cent	27.5			
Cold Bending Test— Angle before fracture	180 degr. good			
Dates when Inspected	22.7.29.			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

The material has been ordered to special requirements.

Fee (if any chargeable) £

To be paid at Düsseldorf.

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

Flag's Register of Shipping.

Order: 264.74.

(Report on Machinery) No. 145.

No. 2887. ENGINE FORGINGS XXXXXXXXXXXXXXX

I have to report that the Forgings XXXXXXXX as herein described, manufactured

by Messrs. Henschel & Sohn A.G. of

for the Engines No. XXXXXXXX being constructed by Messrs. Kockum & Verkerke A.B.

of Malmö for the Ship No. 2887, being built by

have been inspected by me as set forth below, and found to be so far as can be seen, sound and free from defects. These have been despatched to

Malmö.

Düsseldorf 23rd July 1929.

2407.

V.8.23.7.29.

THRU SHAFT

INTERMEDIATE SHAFT

XXXXXXXXXX

1 valve ring

XXXXXXXXXX

Annealed Stem. Mart. rolled Iron Steel

rolled

Yes

1420x76

Examined finished at Malmö.

Tough turned

798 6x4

35.2

27.5

180 gear. good


22.7.29.

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS

The material has been ordered to special requirements.

to be held at Düsseldorf.

It is to be noted that the Open Market price



Register Foundation