

# Lloyd's Register of Shipping.

(Report on Machinery, No. \_\_\_\_\_ Port \_\_\_\_\_)

No. 13557 ENGINE FORGINGS ~~OR CASTINGS~~.

I have to report that the Forgings ~~or Castings~~, as herein described, manufactured by J. Brown & Co Ltd of Sheffield for the Engines No. 463 being constructed by Harland & Wolff of Belfast for the Ship No. \_\_\_\_\_, being built by \_\_\_\_\_ of \_\_\_\_\_

has been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to \_\_\_\_\_

The words FORGINGS or CASTINGS should be struck out as may be required.

Mark on Forgings or Castings.

Lloyd's  
No. \_\_\_\_\_  
16.1.24

1 Connecting Rod  
N<sup>o</sup> 2625.

J. Hodge  
Sheffield  
9.4.24

	<del>CRANK SHAFT.</del>	<del>THRUST SHAFT</del>	<del>INTERMEDIATE SHAFT</del>	<del>TUBE SHAFT</del>
	<del>FLYWHEEL SHAFT.</del>			<del>SCREW SHAFT</del>
Material* ...		<u>Siemens Steel</u>		
How made ...		<u>Forged.</u>		
If Annealed ...		<u>Yes</u>		
Dimensions, Forgings				
Weight, Castings				
Progress on Inspection }		<u>Rough Machines</u>		
Tests on Standard Test Pieces.		<u>N<sup>o</sup> 2625.</u>		
Tensile Test—		<u>30-8</u>		
Tons per square inch		<u>34.0</u>		
Extension per cent		<u>180°</u>		
Cold Bending Test—		<u>22.4.24 - 1.4.24</u>		
Angle before fracture				
Dates when Inspected				

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £

To be paid at

\* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



© 2019

Lloyd's Register

W 46-0236