

6. For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office \_\_\_\_\_ 19

# Lloyd's Register of Shipping.

(Report on Vessel No. \_\_\_\_\_ Port Hamburg.)

No. 899. SHIP ~~XXXXXXXXXX~~ CASTINGS.

I have to report that the undermentioned ~~XXXXXX~~ Steel ~~XXXXXXXXXX~~ Castings, manufactured by Messrs. Blohm & Voss of Hamburg for the Vessel No. S.S., being built by "Simon Bolivar" have been inspected by me as set forth below and found to be, so far as can be seen, One Rudder main piece, sound and free from surface defects.

See on ~~XXXXXX~~ Castings.

Lloyd's  
No. 72.  
F.O.10.4.34.

Hamburg, 10th of April 1934.

*Friedrich Ohlgen.*

	STERN FRAME.	RUDDER <sup>main piece</sup> <del>XXXXXX</del>	STEM.
Material*	Annealed S.M. Cast Steel.		
How made	cast.		
Annealed	Yes.		
Dimensions	To Sketch.		
Progress on Inspection	rough, turned & finished.		
Date when Inspected	29.3.34.-10.4.34.		
CASTINGS.	.798	3"	
Tests on Standard Test Pieces.			
Tensile Test—			
Tons per square inch	34,5	33,6	
Extension per cent. ...	28,0	25,5	
180 Bending Test—	180 degr. good.		
Angle before fracture	7 feet.		
Drop Test—	satisfactory.		
Height from ground ...			
Hammering Test—			
If made according to Rules and found satisfactory ...			

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.



Fee (if any chargeable) £ : :  
To be paid at \_\_\_\_\_



© 2019

Lloyd's Register

If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.

1,30. T.

W 478 00 76

Travelling

THE SURVEYORS ARE REQUESTED NOT TO WRITE ACROSS THIS MARGIN.