

Lloyd's Register of Shipping.


RESULTS OF TESTS OF STEEL.

Made by Sir W. G. Armstrong Whitworth & Co. Ltd of Manchester.
For ~~South S. S. Co. Ltd of Newcastle~~
Fletcher of Kinghorn

Date of Test.	Batch No.	Test No.	Change Mark.	Thickness.	Breadth. Dia	Area. sq. in.	Tons, Total.	Tons per square inch.	Extension in 8 ins. %	Bend.
1 Rudder Head		17894/4			564	28	✓	31.0	36	180°
1 M. S. Plate		17781A3			"	"	✓	29.8	34	180°
1 Main Post		17754A1			"	"	✓	30.0	33	180°
2 Rudder Arms (3+5)		17777C2			"	"	✓	29.2	37	180°
1 " Arm (1)		B3			"	"	✓	"	"	"
1 " " (2)		17853A1			"	"	✓	30.0	34	180°
1 " " (4)		A2			"	"	✓	"	"	"

Cold bend tests satisfactory

Alfred H. Lane.



© 2019

Lloyd's Register
Foundation