

Lloyd's Register of British & Foreign Shipping.

L. 29094, 29095
29095a

(Report on Vessel No.

Port

No. 201 SHIP ~~FORGINGS OR~~ CASTINGS.

I have to report that the undermentioned ~~Iron or Steel Forgings or~~ Castings, manufactured by Messrs. *Skoda Werke Act. Ges.* of *Pilsen* for the Vessel No. *238*, being built by Messrs. *J. C. Teichlenborg* of *Geestemünde* have been inspected by me as set forth below and found to be, so far as can be seen, *sound and free from defects*

- 1 *Stemshce*
- 1 *Stemframe in two parts*

on Forgings.

Lloyd's

No. *613,612*
4.75 5.10

Vienna 22nd May 1910
W. Roth

	STERN FRAME.	RUDDER FRAME.	STEM.
Material	<i>Annealed S. M. Steel</i>	/	<i>Annealed S. M. Steel</i>
Made	<i>cast</i>		<i>cast</i>
Dimensions	<i>9 1/2" x 7 1/2"</i>		<i>10 1/2" x 6 1/16"</i>
Condition on Inspection	<i>finished</i>		<i>finished</i>
When Inspected	<i>18/4.1910</i>		<i>18/4.1910</i>
	<i>17/5.1910</i>		<i>17/5.1910</i>

PLATES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS, OR PARTICULARS OF TESTS APPLIED TO CASTINGS.

Results of Tests

Stem - 35.0 Tons per square inch; 26.3% elongation in 3"
32.3 " " " " " " ; 29.0% " " "

2 Stemframe

Bottom part - 30.9 Tons per square inch; 32.0% elongation in 3"
" " 28.5 " " " " ; 31.6% " " "
Top part - 28.7 " " " " ; 31.6% " " "
" " 28.5 " " " " ; 31.0% " " "

Fee (if any chargeable) £

To be paid at *Vienna*

Bends satisfactory

* If of Iron, state whether scrap or puddled Iron.

