

B. no 1510  
Order no 10311

# Lloyd's Register of Shipping.

Book of  
Link den 19 JUL 1926

Surveys Office, DÜSSELDORF.

to certify, that Julius Krauss the undersigned surveyor to this society tested in  
works of Messrs. Hammermannrohren-Werke Akt. G. m. b. H. of Heilbronn  
unmatted Siemens Martin Boilersteel plates specified hereunder, ordered  
Messrs. Kockmann u. Verkestrade A. B. of Wolm  
the ship No. 151 Boiler No. 842-843 and that the results of tests were as are set forth below.

Dimensions. in mm			Intended for	Sample number	Charge number	Tensile tenacity kg. p. sq. mm			Elongation in 200 mm. in %	Bending tests		Remarks.
Length.	Breadth.	Thick- ness.				As per rules.	Ord- ered.	By test.		Cold.	Tem- pered.	
2430	3240	23 1/2	Shell pl.	232.	7569	44/50	44/50	49.-	23	good	good	
"	"	"	"	236.	"	"	"	50.1	21	"	"	
"	"	"	"	242.	"	"	"	49.-	24	"	"	
"	"	"	"	246.	"	"	"	48.8	24	"	"	
3010	"	"	"	292.	7584	"	"	46.3	26	"	"	
"	"	"	"	296.	"	"	"	46.2	27	"	"	
386	3130	22	Butt strap	22	7384	"	"	47.6	26	"	"	
"	3240	20	"	28	7384	"	"	47.3	28	"	"	
"	"	"	"	21	7569	"	"	50.-	22	"	"	
For sketches	24		Front end pl.	15	7603	41/47	41/47	43.7	27	"	"	41
"	"	"	"	14	"	"	"	45.1	27	"	"	42
"	"	"	Back end pl.	13	"	"	"	42.5	28	"	"	43
"	"	"	"	13	"	"	"	43.8	28	"	"	44
"	"	20	Trice plate	19	7528	"	"	41.2	28	"	"	33
"	"	"	"	"	"	"	"	"	"	"	"	34
"	"	"	"	"	"	"	"	"	"	"	"	35
"	"	"	"	"	"	"	"	"	"	"	"	36
"	"	17	Crown ch. back pl.	20	7528	"	"	43.5	26	"	"	37
"	"	"	"	"	"	"	"	"	"	"	"	38
"	"	"	"	"	"	"	"	"	"	"	"	39
"	"	"	"	"	"	"	"	"	"	"	"	40

This Certificate is issued upon the terms of the Rules and Regulations of the Society, which provide that:—  
While the Committee use their best endeavours to ensure that the functions of the Society are properly executed, it is to be understood that neither the Committee nor the Society are under any circumstances whatever to be held responsible for any inaccuracy in any report or certificate issued by the Society or its Surveyors, or in any entry in the Register Book or other publication of the Society, or for any error, omission, default, or negligence of the Surveyors, or other Officers or Agents of the Society.  
—Material with less than 26 Tons tensile strength may not be used in the construction of boilers for classed vessels, unless specially sanctioned by the Committee.  
1 Ton per square inch = 1,574 Kilo per square millimeter. 1 Kilo per square millimeter = 0,635 Tons per square inch.

6: Y2 Y6. for Messrs. Rocklunds msk. Verkstads A.B. Malmö. G. 151 B. 872-873.

Dimensions. <i>in mm</i>			Intended for	Sample number	Charge number	Tensile tenacity <i>Kg. p. sq. mm</i>			Elongation in 200 mm. <i>in %</i>	Bending tests		Remarks.
Length.	Breadth.	Thick-ness.				As per rules.	Ord-ered.	By test.		Cold.	Tem-pered.	
4445	690	17	Comb. sh. sides	25	Y605	41/47	41/47	44.3	27	good	good	
1405	700	19	" "	27	Y404	"	"	43.3	28	"	"	
For sketch		13	Corrug. furnace	17	Y513	41/47	41/47	43.9	28	"	"	48
"	"	"	" "	"	"	"	"	"	"	"	"	50
"	"	"	" "	16	Y513	"	"	44.-	28	"	"	47
"	"	"	" "	"	"	"	"	"	"	"	"	49
850	720	23 1/2	" "	18	Y584	44/50	44/50	45.2	27	"	"	45
"	"	"	" "	"	"	"	"	"	"	"	"	46
Ø	220	12	" "	26L	Y442	"	"	47.-	24	"	"	
Ø	150	12	" "	26B	"	"	"	47.-	24	"	"	
600	490	16	" "	30	Y442	"	"	47.7	26	"	"	

*Witnessed 16<sup>th</sup> July 1926.*

*Jul. Quast*

Surveyor to Lloyd's Register

WS48-0182 2/2

Lloyd's Register of Shipping  
 Received.  
 MALMO  
 20-12-26

