

# Lloyd's Register of Shipping.

## RESULTS OF TESTS OF STEEL.

Made by Messrs Stabilimento Metallurgico DELTA -Cernigliano L.-

For S/S "AUSONIA" (Yard N°283) . -

Date of Test.	Batch No.	Test No.	Charge Mark.	Thickness Length	Breadth. Diam.	Area.	Total, Tons.	Tons per square inch. 6m/m.	Extension in 8 ins. %
18/3/27)	C.451	153	--	80	20	314	7.6	15.37	20
22/3/27)		154	--	80	20	314	7.5	15.18	18.7

Bend and destruction tests satisfactory.

Representing 56 cast naval brass frames and glass holders intended to be fitted on the S/S "AUSONIA" . -

GENOA, August 24th 1927

(Sgd) E. R. Morrison for  
G. de C. Ballardie  
Surveyors to Lloyd's Register.



© 2021

Lloyd's Register  
Foundation

WS49-0093