

Lloyd's Register of Shipping.

RESULTS OF TESTS OF STEEL.

Made by Messrs Stabilimento Metallurgico DELTA - Cornigliano L.

For S/S "AUSONIA" (Yard N°283). -

Date of Test.	Batch No.	Test No.	Charge Mark.	Thickness Length	Breadth Diam.	Area.	Total Tons.	Tons per square inch /m/m.	Extension in 20 cm. %
10/5/27 } 13/5/27 }	F.998	1	--	50	14.8	172	7.5	27.65 30.16	14
		2	--	50	15	177	8.4	43.6 47.5	20
	F.999	3	--	50	15	177	8.1	28.87 45.5	26
		4	--	50	15	177	7.9	28.32 44.6	32
	F.1000	5	--	50	15	177	7.9	28.32 44.6	32
		6	--	50	15	177	8	28.76 45.3	30

Representing forged naval brass hinged pins and securing bolts intended for the S/S "AUSONIA" (Yard N°283). -

GENOA, August 24th 1927

(Sgd)

E. R. Morrison
G. de B. Ballarvie

Surveyors to Lloyd's Register. -



© 2021

Lloyd's Register
Foundation