No. 191

LLOYD'S PROVING HOUSE, CARDIFF.

(LICENSED BY THE BOARD OF TRADE.)

13 Nov 1909

The following are the results of testing one samples of Steel. tobe in the presence of Mr. John Dykes Lloyds Surveyor received from Messrs. W. Sisson & Co. Gloucester

Description of Sample.	Number of Sample.	Particulars of Samples. Size. Inches.	Particulars of Samples. Area. Sq. Inches.	Ultimate Stress. Total. Tons.	Ultimate Stress. Per Square Inch of Original Area. Tons.	Fractured Section. Size. Inches.	Fractured Section. Area. Sq. Inches.	Reduction of Area. Sq. Inches.	Reduction of Area. Per Cent.	Extension taken in Inches.	Extension. Actual.	Extension. Per Cent.	Appearance of Fracture.	Remarks.
1/9x3 GT T.S.	1	.798	.500	15.25	30.5	.64	.321	.179	35.8	3	.93	31.0	Part granular & Silky	Machined

Cold Bending Test satisfactory

The above tests were made in my presence.
Bend test according to rule Satisfactory.
John Dykes 12/11/09

5th February 1910

Wm. Parr. Superintendent

W598-0013

© 2020 Lloyd's Register Foundation